

DESCRIPTION

Total thickness	EN 428	mm	2.50
Thickness of wearlayer	EN 429	mm	1.02
Weight	EN 430	g/m ²	2660
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20

CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
Fire rating	EN 13 501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test oil (1)	DIN 51 130	class	R10




PERFORMANCE

Wear Resistance	EN 660.2	mm ³	≤ 2.0
Wear Group	EN 649	-	T
Type Binder content	ISO 10582	type	I
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation (requirement)	EN 433	mm	≤ 0.10
Residual indentation (value)	-	mm	≈ 0.03
Impact sound insulation	EN ISO 717-2	dB	8
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	Protecsol®2
Chemical products resistance (2)	EN 423	-	OK
Anti-bacterial activity (E.coli – S. aureus – MRSA) (3)	ISO 22196	-	> 99% inhibits growth

ENVIRONMENT / INDOOR QUALITY AIR

TVOC after 28 days	ISO 16000-6	µg/m ³	<10
Certification	-	-	Floorscore™

MARQUAGE CE

	<p>EN 14041</p>	
		

(1) For lifetime sustainable wet resistance, please refer to Tarasafe ranges.
(2) Regarding the resistance to chemicals, please download the corresponding leaflet from our website
(3) The implementation of an effective cleaning method is the best defence against infection.